

INVITATION FOR BIDS
CLOSING BID DATE- MARCH 11, 2022
TOWN OF MEEKER
345 Market Street
MEEKER, CO 81641

You are invited to bid on the Town of Meeker Crack Seal project. Bids will be to clean cracks, furnish and install approximately 20,000 pounds of hot-pour, Deery American Super stretch 974, in the Town of Meeker (Please refer to Specifications).

Sealed bids will be accepted until Friday March 11, 2022 at 2:30 p.m. The Town Board of Trustees will open bids at their regular board meeting on Tuesday, March 15, 2022 at 7pm at Town Hall (basement) 345 Main Street, Meeker. Bids will be awarded at the following regular board meeting on Tuesday, April 5, 2022. The successful bidder must maintain workers compensation, general liability insurance in the amount of no less than \$1,000,000.00 during the project.

The Town reserves the right to reject any and all bids and waive any and all informalities, and the right to disregard all nonconforming or conditional bids or counter proposals. Contract award and preference will be based upon The Town of Meeker Personnel Policy and Procedures manual, entitled "Contracts-Award-Preference". More Information is Available from Russell Overton (970)878-5530 or 878-5344.

Sealed bids shall be mailed or delivered to Town of Meeker, 345 Market St., Meeker, CO 81641 and "Meeker 2022 Hot Pour Crack Filling Project Bid" shall be written upon the front of the envelope. Specifications are available at Town Hall, 345 Market St., Meeker, CO 81641 or on our website at www.townofmeeker.org or requested by telephone at (970)878-5344.

THE BOARD OF TRUSTEES
OF THE TOWN OF MEEKER
Mandi Etheridge, Town Administrator

CRACK SEALING SPECIFICATIONS

Crack sealing Specifications:

DESCRIPTION

The work of this section shall consist of furnishing and installing a pre-approved rubberized crack sealer in properly prepared cracks in bituminous paved surfaces.

MATERIAL

The material shall be hot poured rubberized crack sealer (Deery American 974 or equal
The material shall conform to the requirements of ASTM D-3407 for hot poured elastic type sealant.

The sealant shall be delivered in the manufacturers sealed containers. Each container shall be legibly marked with the manufacturer's name and trade name of the material.

Materials from different manufacturers other than stated above shall not be allowed. The supplier shall issue a certificate of compliance stating that the material meets the requirements of this project.

Construction Requirements

Equipment: Heating pots for hot poured sealant shall be an indirect double boiler type using oil heat transfer medium. The heating pot shall be capable of controlling the temperature of the sealant within the manufacturers recommended application range. A thermometer calibrated within +/-5 degrees Fahrenheit for range of 200 to 500 degrees Fahrenheit shall be provided. The heating pot shall be capable of constantly agitating the material.

All cracks larger than 1/8 inch and less than one inch in width are to be sealed.

Weather Limitations

Sealant shall not be placed when the weather is foggy, raining, or when the surface to be sealed is damp or wet.

Preparation

Immediately prior to the placement of the sealant, the cracks shall be blown clean of dirt, debris, or foreign matter to a depth of at least twice the width of the crack but to a depth of no greater than the pavement thickness.

Application

The sealant shall be heated according to the manufacturer's recommendations, applied at the manufacturer's temperature and installed flush with the pavement surface. Immediately after the crack is filled, excess material shall be leveled off of the surface by a squeegee, a shoe attached to the applicator wand, or other suitable means. The squeegeed material shall be centered in the crack and shall not exceed 3 inches in width nor 1/16 inch above the surface of asphalt. Any crack sealer showing settling, shrinkage, or a depression in excess of ¼ inch below the pavement surface shall be refilled.